



FICHA TÉCNICA

Zorpit-TWALL Transparent Sealing

DESCRIPTION

Colourless monocomponent-liquid-based solvents and siloxanes. For use on vertical or inclined surfaces which are absorbent.

APPLICATIONS

Especially suitable for vertical or inclined surfaces.
-For Waterproofing bricks, mortars, ceramic tiles, natural and artificial stones
Q: For the treatment and protection of terracotta.

USAGE AND DOSAGE

Surfaces must be clean and dry.
Can be applied with brush, roller or airless.
Apply a layer and cover completely the surface.
* For added security we recommend a second lighter layer, right after the surface has absorbed the first layer and before it is totally dry.
The maximum capacity of waterproofing can be reached 24 h after application.
Depending on the absorbency of the surface the usual expense is set between 4 and 7 square meters per litre per layer. Nevertheless it is advisable to perform a preliminary test to determine how much will be spent.

Surface: The surface should be sanitized, clean, dry and free of dust and grease.
-For Bricks, we recommend two to three days of drying after cleaning.
-Metal surfaces must be free of rust.



PROPERTIES

-Fully repels water and external moisture, allowing the passage of water vapor.
-Inert treatment with high oxidation resistance to chemical attacks, as well as fungi, bacteria, etc.
-Density 20 ° C: 0.8 g / cm.
-Aspect: colorless liquid.
-Drying (20 ° C) 1 hour.

PRECAUTIONS

-Do not smoke, take drinks or eat during handling.
-Use gloves, mask and eye protection.
-For Disposal follow local and national regulations.
-Flammable.
-Product: Stir well before use. Can be applied with brush or roller, although the application with wide brush allows a better finish because it allows spreading the product evenly.

This Technical data sheet, such as recommendations and information given serves only to describe, Usage and product applications. The data and information provided are based on our expertise, laboratory tests and practical experience. The recommended dosages are based on our own experience, but however these may vary according to the different usgae conditions. Actual measurements should be determined in the work itself through pretests and are the sole responsibility of the customer. Product usage that is not adjusted to the recommended is not of our responsibility. Our technical service will be at your disposal for any further advice. There is a safety sheet available. This document cancels the previous editions. Date of last update: 03/03/2010